

## General Finishes Water-Based Primer & Sealer Product Comparison



** *** *** ***	compare GF products.	
Stain Blocker	Enduro® White Undercoat	Enduro® Sanding Sealer
WATER BASED.  STAIN BLOCKER WHITE PRIMER  LIMITATION OF THE PRIMER	ENDURO  ENDURO  EV GENERAL INIGNE  WHITE  UNDERCOAT  WAS A SERIE ALL AND	ENDURO  VI GENERAL TINISHE  SANDING SEALER  MINISTER AND BEED OFF
Interior Stain-Blocking Primer	High-Build Primer	Fast Build, Easy to Sand, Economic Price
SUGGESTED USE	SUGGESTED USE	SUGGESTED USE
Furniture, Cabinets, Millwork	Furniture, Cabinets, Millwork	Furniture, Cabinets, Millwork
PRODUCT COLOR	PRODUCT COLOR	PRODUCT COLOR
White (Drys Gray)	White	Water White (Dries Clear)
TINTABLE	TINTABLE	TINTABLE
No	White & Lights Only	Yes
AMBERING	AMBERING	AMBERING
No	No	No
INTERIOR OR EXTERIOR	INTERIOR OR EXTERIOR	INTERIOR OR EXTERIOR
Interior Only	Interior & Exterior	Interior Only
ТҮРЕ	ТҮРЕ	ТҮРЕ
Epoxy Acrylic Stain Blocking Primer	Acrylic White Primer	Acrylic Clear Coat
CAN SIZES	CAN SIZES	CAN SIZES
Quarts, Gallons	Gallons, 5-Gallon Pails*	Quarts, Gallons, 5-Gallon Pails*
COVERAGE	COVERAGE	COVERAGE
500-600 Sq.Ft./Gal.	450 Sq.Ft./Gal.	600 Sq.Ft./Gal.
COATS	COATS	COATS
2 Coats	1-2 Coats	1-2 Coats
APPLICATION	APPLICATION	APPLICATION
Brush, Roll, Spray	Spray	Spray
OVER EXISTING FINISHES	OVER EXISTING FINISHES	OVER EXISTING FINISHES
Yes	Yes	Yes
TIP SIZE	TIP SIZE	TIP SIZE
HVLP 1.8mm-2.0mm	HVLP 1.5mm-1.8mm	HVLP 1.1mm-1.3mm
DRY TIME - TOUCH	DRY TIME - TOUCH	DRY TIME - TOUCH
1+ Hr.	30+ Min.	10+ Min.
DRY TIME - RECOAT	DRY TIME - RECOAT	DRY TIME - RECOAT
2+ Hr.	2+ Hr.	2 Hr.
STACK TIMES - 70°F, 50% RH	STACK TIMES - 70°F, 50% RH	STACK TIMES - 70°F, 50% RH
12+ Hrs. Dependent on Conditions	8+ Hrs. Dependent on Conditions	8+ Hrs. Dependent on Conditions
VISCOSITY	VISCOSITY	VISCOSITY
Thick	Thick	Medium
WEIGHT SOLIDS	WEIGHT SOLIDS	WEIGHT SOLIDS
35%	53%	30%
VOLUME SOLIDS	VOLUME SOLIDS	VOLUME SOLIDS
44%	33%	25%
voc	voc	voc
<80 g/L	<90 g/L	<250 g/L
	<u>~</u>	<u> </u>



